

**GHL inc.**785, rue Paul Lussier
Ste-Helene de Bagot
Qc, Canada, J0H 1M0Phone: (450) 791.2222
Toll free: 1 (888) 791.2223
Fax: (450) 791.2225E-mail: ghl@ghlinc.com
Website: www.ghlinc.com

**GREEN-LINED WOVEN POLYPROPYLENE (115 g/m²)
GROUND COVER
(black or white)**

TEST REPORT

Product	Ground Cover	Size	115g/m ²	
Sample				
Test #	Spot check	Date	2016.04.06	
#	Test element	Unit	Result	Remarks
1	Weight	g/m ²	115.1	Pass
2	Tear resistance (MD)	kN/m	20.1	Pass
3	Tear resistance (CD)	kN/m	15.7	Pass
4	Elongation (MD)	%	15.8	Pass
5	Elongation (CD)	%	15.9	Pass
6	CBR Mullen Bursting force	kN	1.63	Pass
7	Trapezoidal tear resistance	mm	0.23	Pass
8	Coefficient of vertical permeability	cm/s	2.3x10 ⁻³	Pass
9	Equivalent opening O ₉₀	mm	0.17	Pass
Standard : GB/T17641-1998				